

## TIB KAT<sup>®</sup> 216

**TIB KAT 216** is a liquid tin catalyst based on dioctyltin compounds. This raw material basis gives improved toxicological properties compared with dibutyltin derived catalysts.

Main applications for TIB KAT 216 are:

- catalysis of polyurethane-reactions
- curing of silicone-resins and RTV Silicones
- transesterification and esterification reactions
- stabilizer for PVC.

The dosage of **TIB KAT 216** is depending on the application, normally between 0.1 - 1 wt.-%.

Product Data	
Chemical formula	(C <sub>8</sub> H <sub>17</sub> ) <sub>2</sub> Sn(OOCC <sub>11</sub> H <sub>23</sub> ) <sub>2</sub>
CAS No.	3648-18-8
Molecular weight	approx. 744 g/mol
State of aggregation	clear liquid at room temperature (>20°C)
Melting point	> 10°C
Solubility	soluble in organic solvents

Specification	
Tin content	15.5 – 17.0 %
Density (20°C)	1.01 - 1.03 g/cm <sup>3</sup>
Colour (Gardner)	≤ 3

## Storage

**TIB KAT 216** can be stored for at least one year if kept closed in the original packaging; sensitive to frost.

## **Packaging**

50 kg, 220 kg plastic drum and 1.000kg IBC, other packaging size upon request.

## Special advice for security

- Information concerning classification and labelling according to the regulations governing transport and hazardous chemicals
- · protective measures for storage and handling
- safety measures in case of accident and fire toxicity and ecological effects

is given in our material safety data sheets.

**Customs Tariff Number: 2931 9000** 

Issue / Oct 16

TIB Chemicals AG | Mülheimer Strasse 16 -22 | D-68219 Mannheim | P.O. Box 81 02 20 | D-68202 Mannheim Phone +49 (0) 621 8901- 811 | Fax +49 (0) 621 8901- 475 | info.@tib-chemicals.com | www.tib-chemicals.com



This information is given to the best of our knowledge but without obligation. We are not liable for any wrong advice or any advice we may have failed to give. This data sheet becomes invalid as soon as a new edition has been published. Please contact us for latest.