



KaMin LLC
822 Huber Road
Macon GA 31217
Main 478-750-5410
www.kaminsolutions.com

ASP[®] 200

Hydrous Aluminum Silicate

Product Description

ASP[®] 200 kaolin is a very fine particle-size, standard brightness grade of aluminum silicate. It is highly pulverized and is chemically inert.

Application Information

ASP 200 kaolin is recommended for use in solvent-borne and water-borne primers and topcoats, as well as for use in industrial, coil, appliance and various undercoats. It is also widely used in electro-deposition paints. ASP 200 kaolin provides a good level of reinforcement in a wide variety of polymeric systems. Recommended for use in polyester pultrusion profiles. Typical applications include solvent-borne topcoats and primers, pultrusion profiles, water-borne topcoats and primers, BMC/ SMC, OEM electro-deposition coatings and primers.

Physical Properties	Typical Value
Physical Form	Highly Pulverized Powder
GE Brightness (%)	86
Screen Residue, 325 Mesh (%)	0.01
Free Moisture (%) measured at 105°C	1.0
pH (20% solids)	4
Median Particle Size, Sedigraph (µm)	0.4
Specific Gravity (g/cm ³)	2.58
Bulk Density, Loose lb/ft ³ (kg/m ³)	18 / 290
Bulk Density, Tamped lb/ft ³ (kg/m ³)	30 / 480
Oil Absorption, Rubout (ASTM D-281)	43

Revised October 2022

KaMin[®] LLC, KaMin[®] and the KaMin[®] logo are registered trademarks of KaMin[®] LLC. The above data are representative data for this product and should not be perceived as specifications or maximum/minimum values. The information contained herein is believed to be accurate and reliable, but KaMin[®] MAKES NO WARRANTIES OR MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, OR ANY OTHER EXPRESS OR IMPLIED WARRANTY. The information herein relates only to the specific product described and not to such product in combination with any other product. Providing information as herein contained is not to be regarded by implication or otherwise as conveying any rights or permission for use which would violate any patent rights or violate any law, safety code or insurance regulation. Natural mineral products are subject to the normal variations related to the deposits from which they are mined.

