

AGITAN[®] P 841

TECHNICAL INFORMATION

Powder defoamer

Composition:	Blend of defoamer components on silica	
Appearance:	powder	
Colour:	white	
Typical Properties:	Ash:	approx. 42 %
	Consistency:	free flowing powder
	Apparent density:	approx. 540 g/l
	Solubility in water:	dispersible in water

This information is intended as a guideline only and should not be used to issue specifications. Slight deviations do not affect application and capability of the product. For specifications please consult the Certificate of Analysis.

Properties/applications: AGITAN P 841 is recommended for application in dry blends which are dissolved in water before application. The addition of AGITAN P 841 results in low foaming solutions, specifically aqueous pastes or masses with very low air content. In some mortar systems AGITAN P 841 shows a plasticizing effect, meaning the spreading value is increased. This is ideal for jointless flooring compounds. In some systems setting time is prolonged but curing time is not influenced.

Main applications:
- Joint fillers and putties
- Leveling compounds
- Screeds (cement and anhydride based)
- Gypsum
- Cement
- Mortars
- Powder paints
- Adhesives

Recommended levels/use: Ladder studies are recommended to determine optimum concentration level. Normal dosage ranges from 0.1 to 1 % on finished product. Handling of AGITAN P 841 is particularly convenient with respect to flowability, dusting and ease of incorporation.

Storage/handling: AGITAN P 841 is not sensitive to freezing. For better handling it should be stored dry between 15 and 25 °C. The minimum shelf life in closed containers is 15 months from the date of manufacture.

Packaging: Pallet with 30 bags, 25 kg each (750 kg)

Our technical suggestions are based on data from many experiments and cannot represent a warranty of any kind as to their performance in other formulations. Customers must always verify our product's performance in their own systems. This technical data sheet replaces all previous issues.

EN

Revision: May 2017

MÜNZING CHEMIE GmbH
Münzingstrasse 2
74232 Abstatt

Tel.: +49(0)7131/987-0
Fax: +49(0)7131/987-125
sales.pca@munzing.com
www.munzing.com

