

# NECOWEL 5110

## Cosolvent free, modified alkyd emulsion

### Product properties

---

NECOWEL 5110 is a rheologically and aliphatically PU-modified alkyd emulsion with medium oil length. The emulsion does not contain APEO and is free of VOC and SVOC. The emulsion is neutralized with ammonia.

NECOWEL 5110 offers fast drying properties combined with high gloss as well as good weathering- and yellowing-resistance.

NECOWEL 5110 is especially suited for the formulation of house and trim paints for brush application. Due to the rheological modification of the resin, lacquers based on NECOWEL 5110 exhibit an improved newtonian flow behavior. In most cases, the addition of associative thickeners are unnecessary.

### Application

---

- House and trim paints
- Top coats
- Wood lacquers

### Analytical data

---

- Solid content: 39 – 43 %
- Oil length: approx. 35 %
- Type of oil: spec. fatty acids
- pH-value: 7 – 8
- Neutralizer: ammonia
- Solvent: water

### Packaging and storage

---

- Packaging: 180 kg drum | 900 kg IBC | tank car
- Transportation and storage: Protect from freezing and avoid direct sun
- Minimum shelf life: 6 months in closed original packaging
- Detailed health and safety information please find in the corresponding safety data sheet.

ASK Chemicals GmbH | Reisholzstraße 16-18 | 40721 Hilden | Tel. +49 21171103-0 | specialties@ask-chemicals.com | www.ask-chemicals.com

The following marks are registered by ASK Chemicals GmbH in one or more countries:  
ASKOFEN, ASKOCOAT, BIOLIN, NECOLIN, NECOWEL.

# NECOWEL 5110

## Starting formulation

---

Code No.: 170370 House paint based on NECOWEL 5110

Position	Product	Wt. %	Supplier
A	NECOWEL 5110	64.00	ASK
B	Pigment paste 14448	34.00	ASK
C	Borchi Oxy-coat 1101	0.20	Borchers
D	Byk 1710	0.30	Byk
E	Demin. Wasser	1.50	
		<b>100.00</b>	

Mix A - E

Code No.: 14448 Pigment paste

Position	Product	Wt. %	Supplier
A	Demin. Wasser	22.80	
B	Disperbyk 192	6.50	Bykk
C	Byk 024	0.10	Byk
D	Kronos 2310	70.00	Kronos
E	Orisil 200	0.40	Orisil
F	Acticide MBS	0.20	Thor
		<b>100.00</b>	

Mix A - F under stirring and disperse with dissolver or pearler to a particle size < 10µm.

### Test results:

Open time: 15 min. under standard conditions

Gloss: > 80 GU (Gardner 20°)

Application: Excellent flow and brushability

Early block resistance